

BLANK PAGE



Indian Standard METHOD FOR ASSAYING OF FINE GRADE PALLADIUM

UDC 669.234:543:2



@ Copyright 1967

MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 1

Indian Standard METHOD FOR ASSAYING OF FINE GRADE PALLADIUM

Precious Metals Sectional Committee, SMDC 13

Chairman

Representing

DR M. K. BOSE

India Government Mint (Ministry of Finance),
Calcutta

Members

SHRI B. P. ARORA

SHRI K. L. BANERJEE

DR H. P. BHATTACHARYA

SHRI RAVINDRA S. CHOKSI

SHRI L. C. CURTIS SHRI G. K. NAIDU (Alternate)

SHRI S. N. DANDONA

SHRI P. GOPALAKRISHNAYYA

Dr S. L. Mangi Dr V. M. Kher (Alternate)

SHRI PASHUPATI N. MEHRA
SHRI C. P. MEHTA (Alternate)

SHRI J. A. MEHTA DR V. T. SHETH (Alternate)

SHRI C. R. V. NARASAPPA

SHRI R. T. POPAWALA

Representative

REPRESENTATIVE

SHRI MULCHAND M. SHAH Nation SHRI SURESH P. SONAWALA (Alternate)

Dr A. K. CHATTERJEE, Director (Struc & Met) Arora-Matthey Ltd, Calcutta

National Test House, Calcutta

National Metallurgical Laboratory (CSI Iamshedpur

Ravindra Hareaus Ltd, Bombay

The Hutti Gold Mines Co Ltd, Hutti

All India Handicrafts Board, New Delhi

Tamilnad Jewellers' Federation, Coimbatore

Dental Council of India, New Delhi

Precious and Rare Metals and Minerals, Calcutta,

The Bombay Bullion Association Ltd, Bombay

Kolar Gold Mining Undertaking, Oorgaum P.O. (Mysore)

All India Federation of Jari Industry, Surat

Regional Office of the Gold Control Administrator (Ministry of Finance), Bombay

The Surat Jari Merchants' Association, Surat

National Refinery Pvt Ltd, Bombay

ternate)

Director General, ISI (Ex-officio Member)

Secretary

SHRI S. L. BALI

Deputy Director (Metals), ISI

INDIAN STANDARDS INSTITUTION MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 1

Indian Standard METHOD FOR ASSAYING OF FINE GRADE PALLADIUM

0. FOREWORD

- **0.1** This Indian Standard was adopted by the Indian Standards Institution on 23 June 1967, after the draft finalized by the Precious Metals Sectional Committee had been approved by the Structural and Metals Division Council.
- **0.2** Palladium is finding increasing use in the industry. In order to determine the purity of palladium, it is necessary that a standard method is followed. With this in view, a method of assaying has been given in this standard which shall be found useful both for routine and reference purposes. Palladium in its refined form is likely to contain traces of silver, gold and platinum. While preparing this standard, the presence of these elements has been taken into consideration.
- **0.3** In preparing this standard, the Sectional Committee took into consideration the manufacturing and trade practices followed in the country in this field.
- **0.4** In reporting the result of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS: 2-1960*.

1. SCOPE

1.1 This standard prescribes the method for determining the purity of fine grade palladium as laid down in IS: 3096-1965†.

2. QUALITY OF REAGENTS

2.1 Unless specified otherwise, pure chemicals and distilled water (see IS: 1070-1960‡), shall be employed in the tests.

Note — 'Pure chemicals' shall mean chemicals that do not contain impurities which affect the results of analysis.

^{*}Rules for rounding off numerical values (revised).

[†]Specification for fine grade palladium.

[‡]Specification for water, distilled quality (revised).

3. DETERMINATION OF PALLADIUM CONTENT IN FINE GRADE PALLADIUM

- 3.1 Outline of the Method After the separation of impurities like silver, gold and platinum, palladium is precipitated as dimethylglyoximate, filtered, dried and weighed.
- 3.2 Apparatus sintered glass crucible No. 3 porosity.

3.3 Reagents

- 3.3.1 Aqua Regia one part of concentrated nitric acid (sp gr 1.42) and three parts of concentrated hydrochloric acid (sp gr 1.16).
- 3.3.2 Concentrated Hydrochloric Acid sp gr 1.16 (conforming to IS: 265-1962*).
 - 3.3.3 Sulphur Dioxide Solution saturated.
 - 3.3.4 Ammonium Chloride solid.
 - **3.3.5** Ammonium Chloride Solution 38 percent (w/v).
 - **3.3.6** Dimethylglyoxime Solution one percent (w/v) in water.

3.4 Procedure

- **3.4.1** Transfer 1.000 g of the metal to a 250-ml beaker and dissolve in 50 ml of aqua regia, heating on the hot-plate, if necessary. When solution is complete wash down the sides of the beaker and evaporate the solution to a very small volume. Take up with a small quantity of water and, if there is any precipitate, dilute to 150 ml and allow to stand on a hot-plate for two hours. Filter the solution and wash with hot water acidulated with concentrated hydrochloric acid.
- 3.4.2 Evaporate the solution nearly to dryness three times, using 20 ml of concentrated hydrochloric acid each time. Dilute the solution to 200 ml with hot water and add 10 ml of sulphur dioxide solution with stirring and allow to stand for a few minutes. If any precipitate appears add another 5 ml of sulphur dioxide solution and allow to settle on a hot-plate for a few hours.
- 3.4.3 Filter off the solution and wash the precipitate with hot water containing a little concentrated hydrochloric acid. Evaporate the filtrate to a small volume. Add ammonium chloride to the cold solution until just saturated. Dissolve any undissolved ammonium chloride with a few drops of concentrated hydrochloric acid. Allow to stand for a few hours, filter off the precipitate and wash it with ammonium chloride solution.

^{*}Specification for hydrochloric acid (revised).

IS: 3088 - 1967

3.4.4 Dilute the filtrate to 250 ml in a volumetric flask and take an aliquot of 20 to 25 ml. Dilute to 200 ml and add 10 ml of concentrated hydrochloric acid. Add a slight excess of boiling solution of dimethylglyoxime to the cold solution to precipitate palladium (0.1 g of palladium requires 0.22 g of the reagent). Allow the solution to stand for an hour and filter through a weighed sintered glass crucible No. 3 porosity. Wash the dimethylglyoximate precipitate with concentrated hydrochloric acid and then with hot water. Dry at 110°C to constant weight.

3.5 Calculation

Palladium, percent =
$$\frac{A \times 31.67}{B}$$

where

A = weight in g of the palladium dimethylglyoximate precipitate, and

B = weight in g of sample represented by the aliquot.

PUBLICATIONS OF INDIAN STANDARDS INSTITUTION

INDIAN STANDARDS

Over 4000 Indian Standards, broadly classified under the following main heads, have been issued so far:

Agriculture & Food Chemical Civil Engineering Consumer Products Electrotechnical
Mechanical Engineering
Structural & Metals
Textile

Of these, the standards belonging to the Structural & Metals Group fall under the following categories:

Copper and Copper Alloys
Cranes and Allied Appliances
Design Codes
Ferro-alloys
Foundry
Lead, Zinc, Tin, Antimony and
Their Alloys
Light Metals and Their Alloys
Metallic Finishes
Ores and Raw Materials
Pig Iron, Cast Iron and
Malleable Cast Iron

Precious Metals
Refractories
Solders
Steel Castings
Steel Forgings
Steel Products, Wrought
Steel Tubes and Pipes
Structural Engineering Handbooks
Structural Shapes
Welding
Unclassified

OTHER PUBLICATIONS

(SI Bulletin (Published Every Month)			K.
Single Copy			2-00
Annual Subscription	***	944	15.00
Annual Reports (from 1948-49 Onwards)			2-00 to 3-00 each
Handbook of ISI Publications, 1966	-		5+00

Available from

INDIAN STANDARDS INSTITUTION

Headquarters

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi I Telephones 27 36 11 - 20 Telegrams Manaksansths

Branch Offices

The state of the s			
534 Sardar Vallabhbhal Patel Road	Bombay 7	Telephone	35 70 27
5 Chowringhee Approach	Calcutta 13	4	23-18 23
117/418 B Sarvodaya Nager	Kanpur		3 76 95
54 General Patters Road	Madras 2		8 72 78